



## Bronzing Powder\*\*

\*\* (developed & produced by Eckart; [www.eckart.net](http://www.eckart.net))

**SyriCalm™ CLR (PC), Phytosan™ K**

**FORMULA No. 469.18.1026**

Phase	Trade Name	INCI Name	w/w %	Supplier
A	Synafil S1050	Synthetic Fluorophlogopite	17.0	Eckart
	Softtouch CC6004	Boron Nitride	2.5	Momentive
	Zinc Stearate	Zinc Stearate	7.0	VWR
	Kaolin Powder	Kaolin	13.5	Applichem
	Talc Powder	Talc	15.0	VWR
	Visionaire Lava	Copper Powder, Silica	5.0	Eckart
	Visionaire Amber	Bronze Powder, Silica	30.0	Eckart
B	<b>SyriCalm™ CLR (PC)</b>	Water, Phragmites Communis Extract, Poria Cocos Extract	<b>3.0</b>	<b>CLR</b>
	<b>Phytosan™ K</b>	Water, Glycerin, Glycine Soja (Soybean) Seed Extract	<b>3.0</b>	<b>CLR</b>
	Xiameter PMX-200 Silicone Fluid 5cs	Dimethicone	2.0	Dow Corning
	Dow Corning 9040	Cyclomethicone, Dimethicone Crosspolymer	5.0	Dow Corning

### Manufacture

Weigh in phase A and mix with speed mixer (30s/2200rpm). Add phase B to phase A, one after another and mix again with speed mixer (30s/2200rpm). Mix ingredients with a spatula for a short time. Stir with speed mixer (30s/2000rpm) and press powder.



The recommendations and formulations given are based on our knowledge and experience in the field of technical application. They are, to the best of our belief, correct, but are offered without obligation. Those who use our recommendations and formulations as well as those who process CLR Active Agents are themselves responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies.