



High Performance Deo Stick
IV-32.135.06A

<i>Phase</i>	<i>Material Name</i>	<i>US INCI</i>	<i>Supplier</i>	<i>% Material</i>
A	KahlWax 6290 Berry	Rhus Verniciflua Peel Wax	KahlWax	20.00
A	Vegetable Alternative to Beeswax #2	Hydrogenated Sunflower Seed Oil	EFB Biotek	1.50
A	Cutina HR Flakes	Hydrogenated Castor Oil	BASF	2.50
A	CutiBiome CLR™	Octyldodecanol Leptospermum Scoparium Branch/Leaf Oil Piper Nigrum Seed Extract Magnolia Officinalis Bark Extract	CLR	3.00
A	Eutanol G	Octyldodecanol	BASF	33.01
A	Dehymuls PGPH	Polyglyceryl-2 Dipolyhydroxystearate	BASF	2.00
A	Dermosoft GMCY MB	Glyceryl Caprylate	Evonik	0.50
B	Agenaflo 9050	Corn Starch Modified	AGRANA	15.00
B	Sodium Bicarbonate BC EF	Sodium Bicarbonate	Sequens Minerals	15.00
B	Aerosil 200	Silica	Evonik	1.00
B	AnnonaSense CLR™	Annona Cherimola Fruit Extract	CLR	3.00
B	ProRenew Complex CLR™	Lactococcus Ferment Lysate	CLR	3.00
B	Perfume Power Fresh nat.	Fragrance	Voegele	0.49
				100.00

Operating Instructions

Heat up A until completely melted (85°C) with stirring. Add B in this order and homogenize for a short moment. Fill into appropriate container.

Directions for use:

Apply gently under the armpits and then allow to dry.

The recommendations and formulations given are based on our knowledge and experience in the field of technical application.

They are, to the best of our belief, correct, but are offered without obligation.

Those who use our recommendations and formulations as well as those who process CLR Active Agents are themselves responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies.

This formula has been manufactured and stability-tested using a special preservative, but has not been subjected to microbiological challenge tests.

CLR - Chemisches Laboratorium Dr. Kurt Richter GmbH - www.clr-berlin.com